

Clipperlon 2135

Modified PTFE Gaskets



DESCRIPTION

APPLICATION

Steel and enamel flanges, Heat exchanger, Plant / Containers, For high surface stress, For highly aggressive media, For damaged sealing surfaces

CHEMICAL COMPATIBILITY

Particularly for use with aggressive chemicals from pH 0 to 14 (except for molten alkali metals and elemental fluorine gas)

DELIVERY OPTIONS

Flange gaskets and sheets are available in thickness of 1/32", 1/16", 1/8", 0,5mm, 1mm, 1,5mm, 2mm and 3mm.

Other thicknesses available on request.. Standard gaskets can be supplied in accordance with ASME B16.21, EN12560-1 as well as EN1514-1. Non-standard or special gaskets can be manufactured according to customer drawings, or by given sizes or Edrawing.

TEMPERATURE

Can be used from -240°C to approx. 270°C, depending on the installation and operating conditions

APPROVALS & CERTIFICATES

- EC1935 (10/2011)
- FDA 21 CFR 177.1550
- TA-Luft
- EC1935 (10/2011)

- TA-Luft
- FDA 21 CFR 177.1550

SEALING CHARACTERISTICS

- non ageing
- excellent sealability
- low leak rate
- good electrical insulation properties
- outstanding chemical resistance

TECHNICAL DATA

max Temperature [°C]	270
min Temperature [°C]	-240
max Pressure [bar]	40
density [g/cm ³]	0.9
Minimum initial stress [DIN E 2505 part 2] [N/mm ²]	26
Maximum initial stress [DIN E 2505 part 2] [N/mm ²]	160
M-Value	2
Y- Value [psi]	2800
ASTM F36 Recovery [% min]	>12
Gasket required flange roughness [Ra micron]	3,2-6,3
Gasket required flange roughness [RMS]	125-250
max Seating stress [Q _{smax} bei RT EN13555] [N/mm ²]	160
Relaxation PQR (30 MPA 150°C) [%]	0.78
Residual seating stress , [QA=40 MPA, Q _{min} (L 0,01), mg/(s*m) bei RT 40 bar [N/mm ²]	5

LOCATIONS

850 Sense Road LA PORTE, TX 77571, USA GLOBAL HEADQUARTERS

8622 South Choctaw Drive BATON ROUGE, LA, USA 70815

Purnovicka cesta 1026, 01401 BYTCA, Republic of Slovakia EUROPE HEADQUARTERS

PHONE

+1 281 542 0600

+1 225 275 8000

+421 41 553 2686

FAX

+1 281 542 5552

+1 225 273 9073

+421 41 553 2895