

Clipperlon 600

Modified PTFE Gaskets

DESCRIPTION

Leader Clipperlon 600 Joint Sealant is made from 100% pure expanded PTFE. The universal gasket tape forms a thin, but yet strong, reliable gasket under compression, that is highly resistant to aggressive media and chemically inert. Even for the sealing of large, complex and damaged flanges - just peel of the covering paper from the adhesive backing and stick the Joint Sealant tape to the sealing surface - overlap the endings and close the jointing.

APPLICATION

Particularly for use with aggressive chemicals from pH 0 to 14 (except for molten alkali metals and elemental fluorine gas) Pressure up to 40 bar (higher pressures depending on the individual installation), to aggressive media and chemically inert, for the sealing of large, complex and

damaged flanges

CHEMICAL COMPATIBILITY

Particularly for use with aggressive chemicals from pH 0 to 14 (except for molten alkali metals and elemental fluorine gas)

DELIVERY OPTIONS

Gasket Tape Widths from 3 mm to 25 mm, Thickness 1up to 8 mm, Standard Roll Length 5,10 and 25 m

TEMPERATURE

Temperature from -240 °C up to +200 °C

APPROVALS & CERTIFICATES

- USP Class VI (not intended for implantation into the human body) on PTFE
- BAM for gaseous Oxygen
- FDA 21 CFR 175.105 (Adhesive)
- EC1935/EU10/2011
- TA-Luft for steel

components

- TÜV - MUC-KSP-A066
- FDA 21 CFR 177.1550 (PTFE)
- DVGW
- EC1935/EU10/2011
- USP Class VI (not intended for implantation into the human body) on PTFE
- DVGW
- BAM for gaseous Oxygen
- TA-Luft for steel components
- FDA 21 CFR 175.105 (Adhesive)
- FDA 21 CFR 177.1550 (PTFE)
- TÜV - MUC-KSP-A066

• chemical

SEALING CHARACTERISTICS

- reduces scrap and sealing costs
- highly compressible and conformable
- ideal for large sealing surfaces
- easy and quick installation

TECHNICAL DATA

max Temperature [°F]	400
density [g/cm ³]	0.75
Minimum initial stress [DIN E 2505 part 2] [N/mm ²]	18
Maximum initial stress [DIN E 2505 part 2] [N/mm ²]	150
M-Value	1.5
Y- Value [psi]	2500
ASTM F36 Recovery [% min]	3
Gasket required flange roughness [Ra micron]	3,2-6,3
Gasket required flange roughness [RMS]	125-250

LOCATIONS

850 Sense Road LA PORTE, TX 77571, USA GLOBAL HEADQUARTERS

8622 South Choctaw Drive BATON ROUGE, LA, USA 70815

Pšurnovická cesta 1026, 01401 BYTCA, Republic of Slovakia EUROPE HEADQUARTERS

PHONE

+1 281 542 0600

+1 225 275 8000

+421 41 553 2686

FAX

+1 281 542 5552

+1 225 273 9073

+421 41 553 2895

TECHNICAL DATA

max Seating stress [Q _{smax} bei RT EN13555] [n/mm ²]	150
Residual seating stress , [Q _A =40 MPA,Q _{min} (L 0,01), mg/(s*m)] bei RT 40 bar [N/mm ²]	10
compressability, [ASTM F36], [%]	75
ASTM F38 Creep Relaxation [%]	53

LOCATIONS

850 Sense Road LA PORTE, TX 77571, USA GLOBAL HEADQUARTERS

8622 South Choctaw Drive BATON ROUGE, LA, USA 70815

Pšurnovická cesta 1026, 01401 BYTCA, Republic of Slovakia EUROPE HEADQUARTERS

PHONE

+1 281 542 0600

+1 225 275 8000

+421 41 553 2686

FAX

+1 281 542 5552

+1 225 273 9073

+421 41 553 2895