

# Leader Fybar PT 30

## Rubberbonded Fiber Jointing Sheets

### DESCRIPTION

Aramid fibres bound with NBR suitable for general purpose use in hot and cold water, steam, oils, fuels, gases and a wide range of commonly used chemicals.

### APPLICATION

Widely applicable for non-aggressive media such as air, (potable) water, oil, grease and fuel, weak acids and alkalines

### CHEMICAL COMPATIBILITY

### DELIVERY OPTIONS

Flange gaskets and sheets are

available in thickness of 0,5mm, 1mm, 1,5mm, 2mm and 3mm. Other thicknesses available on request.. Standard gaskets can be supplied in accordance with ASME B16.21, EN12560-1 as well as EN1514-1. Non-standard or special gaskets can be manufactured according to customer drawings, or by given sizes or Edrawing.

### TEMPERATURE

Temperature from -30 °C up to +200 °C

- DVGW
- BS7531 Grade Y

### APPROVALS & CERTIFICATES

### TECHNICAL DATA

max Temperature [°C]	250
min Temperature [°C]	-80
max Pressure [bar]	100
density [g/cm <sup>3</sup> ]	1.8
Minimum initial stress [DIN E 2505 part 2] [N/mm <sup>2</sup> ]	40
Maximum initial stress [DIN E 2505 part 2] [N/mm <sup>2</sup> ]	150
M-Value	2.5
Y- Value [psi]	3900
ASTM F36 Recovery [% min]	50
Gasket required flange roughness [Ra micron]	3,2-6,3
Gasket required flange roughness [RMS]	125-250
max Seating stress [Q <sub>smax</sub> bei RT EN13555] [n/mm <sup>2</sup> ]	150
Tensile Strength (quer) DIN 52910 [N/mm]	10

### LOCATIONS

850 Sense Road LA PORTE, TX 77571, USA GLOBAL HEADQUARTERS

8622 South Choctaw Drive BATON ROUGE, LA, USA 70815

Pšurnovická cesta 1026, 01401 BYTCA, Republic of Slovakia EUROPE HEADQUARTERS

### PHONE

+1 281 542 0600

+1 225 275 8000

+421 41 553 2686

### FAX

+1 281 542 5552

+1 225 273 9073

+421 41 553 2895