

# Leader Ring Type Joint RX

## Ring Type Joint Gaskets

### DESCRIPTION

Leader ring type joint flange gaskets (RTJ gaskets) are used in applications that involve extreme pressures and high temperatures. All Leader ring type joint gaskets are manufactured in compliance with API-6A specifications.

### APPLICATION

Ring Joint gaskets are widely used between pipeline flanges, valves and pressure vessels in the Oil & Gas industry; Withstand high pressure situations up to 400 bar (pending on flange construction and rating); Style RX gaskets are suitable for ASME B16.5 flanges up to 2500 lbs. API 6A type 6B flanges can withstand a pressure up to 5000 psi.

### CHEMICAL COMPATIBILITY

Corrosion and chemical resistance are depending on the selected RTJ gasket material. For pressure and temperature range we refer to Technical Specifications, as per table 1.

### DELIVERY OPTIONS

RX shaped RTJ gaskets are available in ring numbers RX20 up to RX215. Customer specific gaskets can be manufactured upon request. Other materials are also available, please refer to table

### TEMPERATURE

Corrosion and chemical resistance are depending on the selected RTJ gasket material. For pressure and temperature range we refer to Technical Specifications, as

per table 1.

### APPROVALS & CERTIFICATES

- ASME B16.20
- API 6A (ISO 10423)
- EN10.204 3.1

### SEALING CHARACTERISTICS

- Interchangeable with a corresponding type R Octagonal Style and type RX number
- Non blow-out type

## TECHNICAL DATA

max Temperature [°C]	See material table below
min Temperature [°C]	See material table below
max Pressure [bar]	400
M-value Soft Iron (D) and Soft Steel (S)	5.5
M-value Stainless steel	6.5
M-value Monel and F5	6
Y-value Soft Iron (D) and Soft Steel (S) [psi]	18000
Y-value Stainless Steel [psi]	26000
Y-value Monel and F5 [psi]	21800
Gasket required flange roughness [Ra micron]	1,6 max.
Gasket required flange roughness [RMS]	63 max.

### LOCATIONS

850 Sense Road LA PORTE, TX 77571, USA GLOBAL HEADQUARTERS

8622 South Choctaw Drive BATON ROUGE, LA, USA 70815

Pšurnovická cesta 1026, 01401 BYTCA, Republic of Slovakia EUROPE HEADQUARTERS

### PHONE

+1 281 542 0600

+1 225 275 8000

+421 41 553 2686

### FAX

+1 281 542 5552

+1 225 273 9073

+421 41 553 2895

## METALLIC MATERIALS

	Identification	Color coding	Temperature Range
	ASME B16.20	ASME B16.20	Degrees C.
Carbon Steel	CRS	Silver	- 25 / + 500
SS304(L)	304(L)	Yellow	- 200 / + 900
SS316(L)	316(L)	Green	- 100 / +550
SS321	321	Turquoise	-200/+550
SS347	347	Blue	-200/+550
Duplex (ASTM A182-F51)	31803	No colour	-60/+300
Avesta 254 SMO (6Mo)	31254	No colour	-100/+550
Carpenter 20 CB3	A20	Black	-100/+500
Nickel 200	NI200	Red	-100/+450
Nickel 201	NI201	Red	-100/+550
Monel® / Alloy 400	MON	Orange	-50/+500
Inconel® / Alloy 600	INC600	Gold	-100/+650
Inconel® / Alloy 625	INC625	Gold	-100/+800
Inconel® / Alloy X-750	INX	No colour	-100/+700
Incoloy® / Alloy 800	IN800	White	-100/+550
Incoloy® / Alloy 825	IN825	White	-200/+800
Hasteloy® / Alloy B2	HAST B	Brown	-100/+500
Hasteloy® / Alloy C276	HAST C	Beige	-100/+600
Titanium	TI	Purple	-100/+350
Zirconium	ZIRC	No colour	-50/+900

### LOCATIONS

850 Sense Road LA PORTE, TX 77571, USA GLOBAL HEADQUARTERS

8622 South Choctaw Drive BATON ROUGE, LA, USA 70815

Pšurnovická cesta 1026, 01401 BYTCA, Republic of Slovakia EUROPE HEADQUARTERS

### PHONE

+1 281 542 0600

+1 225 275 8000

+421 41 553 2686

### FAX

+1 281 542 5552

+1 225 273 9073

+421 41 553 2895